

DOMOFIX-LM

**Solvent-containing
Adhesive for vapour barriers
based on synthetic rubber**

Properties:

- high steam tightness
- high elasticity
- resistant to frost
- strong adhesion
- permanent self-adhesive
- adheres to almost all substrates
- permanent moisture-resistant compound
- adheres to wet and slightly oily substrates

Range of application:

- The adhesive is suitable for the gluing of vapour barriers and vapour locks as well as foils on brickwork and tilework, concrete, wood, plaster, metal.
- remains permanently elastic
- not suitable for polystyrene

Instructions for use:

Surfaces have to be clean, dry, solid and free of grease. Apply a bead of at least 8 mm to the surface. Press the foil onto the bead. Can be used with or without pressure slat. Do not put weight on the building part during the drying process (1 – 2 days).

Packaging:

300 ml cartridge
600 ml plastic bags

Storage:

Shelf life: 2 years at room temperature
Storage temperature: not over 60 °C, resistant to frost

Technical data:

Chemical basis: rubber / soluble resin
 Colour: white, other colours on request
 Density: 0.95 g/cm³
 Drying time: max. 5 - 8 minutes
 Working temperature: + 5 °C - + 50 °C
 Temperature resistance: - 25 °C - + 100 °C
 Capacity: 8 mm x 8 mm: 5 metres per cartridge

Safety note: Flammable. Repeated contact can lead to dry or rough skin. Vapours can cause sleepiness drowsiness. Do not inhale vapour. Avoid contact with eyes or skin. Dispose of empty containers safely.

BADEN-CHEMIE GmbH D-76534 Baden-Baden

(+49 (0) 7223 / 96680

Fax: +49 (0) 7223 / 966850

e-mail: info@baden-chemie.de

www.baden-chemie.de

The publication of this technical data sheet invalidates all previous editions. We guarantee the quality of our material in accordance with our terms and conditions of sale and delivery. On account of the many different substrates and methods of application, we cannot accept liability for the success of the application. Therefore we recommend that preliminary tests for suitability be undertaken by the customer.

10/04